

HOLOGRAFLEX

IRIDESCENTS & RAINBOWS EFFECTS

With shiny finishes (iridescent and rainbow effects), this HTV will illuminate your designs. Available in 6 differents shades of colors as trendy as each other...

| TECH | NICAL DA | ATA | PRODUCT HIGHLIGHTS | | |
|------|------------|-------------------------------------|--|--|--|
| | OMPOSITION | I PU | - - irridescents rainbows effects - Metallic effect | | |
| Ŝ | THICKNESS | 8 0 μm | - Thin product Trendy rainbow patterns - Easy to cut and weed | | |
| | CARRIER | Adhesive & transparent Polyester | | | |
| | | | CARE & MAINTENANCE | | |
| AabA | SIDE | Mirror cutting | Always respect the garment instructions. Wash inside out to extend the design's life. Allow 24 hours after application before first wash. Avoid the use of aggressive products. | | |
| | CUTTING | Flok blade 60° | | | |

- Do not bleach.

| | | | | Washing | Ironing | Tumble-dry |
|-------|-----------------|----------------------------|------|---|--------------|------------|
| T | TEXTILE | Cotton, polyester, acrylic | | 40°C/104°F | Reverse side | Authorized |
| Ö | TIME | 160°C-320°F | | | | |
| ≋₿≋ т | & EMPERATURE | 20s | | | | |
| | PRESSURE | Medium | S | STORAGE Storage life recommendation is up to one year. Store product in dry room with 15°-30°C/ 60°-85°F. Keep away from sunlight, store in a vertical position. | | |
| Z | PEEL | Warm | - St | | | |

| CERTIFICATIONS | STEP BY STEP : HOW TO USE |
|--|--|
| | STEP 1 - Perform a cutting test with your plotter. |
| | STEP 2 - Cut your heat transfer film in mirror, use a blade 60° and weed the excess material. |
| | STEP 3 - Apply design on garment. |
| | STEP 4 - Press and peel warm. |
| NOTE: We highly recommend that you perform tests will change color depending on the exposure to light placed | |
| CHEMICA SAS 🕜 35 rue de Malacussy , 42000 Saint | t-Etienne, FRANCE |
| € Tél : +33(0)477 49 20 90 ⊠ info@chemica.fr | () www.chemica.fr |